

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd – trading as AWTA Product Testing  
A.B.N. 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031  
P.O. Box 240, North Melbourne, Victoria 3051  
Phone (03) 9371 2400 Fax (03) 9371 2499

## TEST REPORT

CLIENT : NOLAN WAREHOUSES  
PO BOX 246  
ROSEBERY NSW 1445

TEST NUMBER : 7-564334-BN  
DATE : 28/01/2009

SAMPLE DESCRIPTION Clients Ref: "Protex Tarpaulin Plain Weave"  
White PVC coated plain weave polyester  
Nom. Comp: PVC/Polyester  
Nom. Mass: 680g/m<sup>2</sup>  
Nom. Thickness: 1.0mm

AS 2755.2-1985 Measurement of flame spread properties of  
vertically oriented specimens

TEST CONDITIONS:	.		Face tested	Face
Barometric Pressure	1014	hPa	Gas used	Propane
Relative Humidity	50	%	Ignition time	5 sec
Burner orientation	Surface		Temperature	23 degC

Test Results:	Length	Width	
Mean Severance Time	.		sec
To 1st marker thread	FTBT	FTBT	
To 2nd marker thread	FTBT	FTBT	
To 3rd marker thread	FTBT	FTBT	
Mean Flame Spread Time			
1st marker to 2nd marker thread	FTBT	FTBT	
2nd marker to 3rd marker thread	FTBT	FTBT	
1st marker to 3rd marker thread	FTBT	FTBT	

FTBT = Failed to burn to

Observations: Length and Width:  
3 specimens failed to burn to 1st marker thread  
3 specimens were tested

No flame reaches the vertical edge of specimen  
No flaming debris fell below the bottom edge of the frame and continued  
to burn

172951

1

( END OF REPORT )

PAGE 1

© Australian Wool Testing Authority Ltd  
Copyright - All Rights Reserved



This Laboratory is accredited by the National Association of Testing Authorities, Australia, for:  
- Chemical Testing of Textiles & Related Products : Accreditation No. 983  
- Mechanical Testing of Textiles & Related Products : Accreditation No. 985  
- Heat & Temperature Measurement : Accreditation No. 1356

This document is issued in accordance with NATA's accreditation requirements. Samples, and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved in advance by the Managing Director of AWTA Ltd.

